

TECHNICAL SPECIFICATIONS

FABIC TYPE: HEAVY CHENILLE

WIDTH: 142 CM

COMPOSITION: 100% POLYESTER

WEIGHT IN GR/M2: 370 GR

TEST RESULTS

|                                |                         |          |                            |
|--------------------------------|-------------------------|----------|----------------------------|
| Tearing strength               | WARP (N)                | 97,8     | ISO 13937-3:2000           |
|                                | WEFT (N)                | 75,9     | ISO 13937-3:2000           |
| Tensile strength               | WARP (N)                | 1291     | ISO 13934-2: 2014          |
|                                | WEFT (N)                | 792      | ISO 13934-2: 2014          |
| Tensile strength               | WARP (N)                | 1690     | ISO 13934-1: 2013          |
|                                | WEFT (N)                | 1065     | ISO 13934-1: 2013          |
| Seam slippage                  | WARP (mm)               | 4        | ISO 13936-2: 2004 200N     |
|                                | WEFT (mm)               | 6        | ISO 13936-2: 2004 200N     |
| Abbrasion resistance           | -Martindale (7200 rubs) | > 50 000 | ISO 12947-2: 20216 - 12kPA |
| Colour fastness to light       |                         | > 4      | ISO 105-B02:2024           |
| Pilling test                   | PILLING                 | 4-5      | ISO 12945-1: 2020          |
|                                | FUZZING                 | 4-5      | ISO 12945-1: 2020          |
|                                | MATTING                 | 4-5      | ISO 12945-1: 2020          |
|                                |                         |          |                            |
| Seam strength                  | WARP (mm)               | 260,9    | ISO 13935-2: 2014          |
|                                | WEFT (mm)               | 291,4    | ISO 13935-2: 2014          |
| Colour fastness to rubbing     | DRY                     | 4-5      | ISO 105-X12:2016           |
|                                | WET                     | 4-5      | ISO 105-X12:2016           |
| Rubbing solvents               |                         | /        | ISO12945-1/2000            |
| Colour fastness to drycleaning |                         | /        | ISO 105-D01:2010           |

WASHING INSTRUCTIONS

Cleaning instruction in case of stains:  
After cleaning with pure water, remove the dirt directly with a tissue and then with a neutreal soap solution.

In case of washing or dry cleaning, low spin drying is always recommended.  
The use of detergent with optical whitener can change the colour.

Avoid dexposure to direct unlight.

